



KINETIC s.r.o

SNP 9/6

796 07 Držovice

+420 582 365 770 kinetic@kinetic.cz



TECHNICAL DATA SHEET

Name :	NEOPREN W8				
Supplier :	KINETIC s.r.o. SNP 9/6 ; 796 07Držovice IČO:27728234 ; DIČ: CZ27728234 tel.: 582 365 770 email : kinetic@kinetic.cz				
Manufactured :	Taiwan				
Polymer Composition (CR/SBR)				CR 100%	
Color				Black	
Elongation at Break (%) (ASTM D412)				400 ↑	
Tensile Strength (Kg/cm²) (ASTM D412)				4.5 ↑	
Tearing Strength (Kg/cm) (ASTM D624)				1.5 ↑	
Hardness (ASKER Type C) (ASTM D2240)				10–12	
Density (g/cm³) (ASTM D1817)				0.20 ± 0.02	
Modulus at 200% (Kg/cm²) (ASTM D412)				1–3	
Water Absorption by Weight (%) (JIS K6767)				2 ↓	
Shrinkage (70°C, 22HRS) (%) (JIS K6767)				2 ↓	
Compression Set (50%, 22HRS 25°C) (%) (ASTM D395)				15–20 ↓	
Flammability Test				UL-94 HBF	
Size (inch)				51"×83" / 51"×98" / 51"×130"	
Laundry symbols :					
	DO NOT WASH	DO NOT BLEACH	DO NOT TUMBLE DRY	DO NOT IRON	DO NOT DRY CLEAN
Suitable method of treatment :	Textile side of the fabric clean either dry with a soft brush or slightly wet cloth The fabric should be left to dry at room temperature				
In Drzovice 25.8.2025					