



KINETIC s.r.o
SNP 9/6
796 07 Držovice
☎+420 582 365 770 kinetic@kinetic.cz



TECHNICAL DATA SHEET

Name :	NEOPREN CS				
Supplier :	KINETIC s.r.o. SNP 9/6 ; 796 07Držovice IČO:27728234 ; DIČ: CZ27728234 tel.: 582 365 770 email : kinetic@kinetic.cz				
Manufactured :	Taiwan				
Polymer Composition (CR/SBR)			CR 12% / SBR 88%		
Color			Black		
Elongation at Break (%) (ASTM D412)			150 ↓		
Tensile Strength (Kg/cm²) (ASTM D412)			6.5 ↑		
Tearing Strength (Kg/cm) (ASTM D624)			2.5 ↑		
Hardness (ASKER Type C) (ASTM D2240)			15–20		
Density (g/cm³) (ASTM D1817)			0.23 ± 0.02		
Modulus at 200% (Kg/cm²) (ASTM D412)			2–4		
Water Absorption by Weight (%) (JIS K6767)			3 ↓		
Shrinkage (70°C, 22HRS) (%) (JIS K6767)			3 ↓		
Compression Set (50%, 22HRS 25°C) (%) (ASTM D395)			20 ↓		
Flammability Test			—		
Size (inch)			51"×83" / 51"×98" / 51"×130"		
Laundry symbols :					
	DO NOT WASH	DO NOT BLEACH	DO NOT TUMBLE DRY	DO NOT IRON	DO NOT DRY CLEAN
Suitable method of treatment :	Textile side of the fabric clean either dry with a soft brush or slightly wet cloth				
	The fabric should be left to dry at room temperature				
In Drzovice 25.8.2025					