



KINETIC s.r.o
SNP 9/6
796 07 Držovice
☎+420 582 365 770 kinetic@kinetic.cz



TECHNICAL DATA SHEET

Name :	NEOPREN WR				
Supplier :	KINETIC s.r.o. SNP 9/6 ; 796 07Držovice IČO:27728234 ; DIČ: CZ27728234 tel.: 582 365 770 email : kinetic@kinetic.cz				
Manufactured :	Taiwan				
Polymer Composition (CR/SBR)					CR 10% / SBR 90%
Color					Černá
Elongation at Break (%) (ASTM D412)					250 ↑
Tensile Strength (Kg/cm²) (ASTM D412)					3.5 ↑
Tearing Strength (Kg/cm) (ASTM D624)					1.5 ↑
Hardness (ASKER Type C) (ASTM D2240)					5–7
Density (g/cm³) (ASTM D1817)					0.24 ± 0.02
Modulus at 200% (Kg/cm²) (ASTM D412)					2–4
Water Absorption by Weight (%) (JIS K6767)					3 ↓
Shrinkage (70°C, 22HRS) (%) (JIS K6767)					3 ↓
Compression Set (50%, 22HRS 25°C) (%) (ASTM D395)					15–25 ↓
Flammability Test					
Size (inch)					51"x83" / 51"x98" / 51"x130"
Laundry symbols :					
	DO NOT WASH	DO NOT BLEACH	DO NOT TUMBLE DRY	DO NOT IRON	DO NOT DRY CLEAN
Suitable method of treatment :	Textile side of the fabric clean either dry with a soft brush or slightly wet cloth				
	The fabric should be left to dry at room temperature				
In Drzovice 14.8.2025					