



**KINETIC s.r.o**  
**SNP 9/6**  
**796 07 Držovice**  
 +420 582 365 770    kinetic@kinetic.cz



## TECHNICAL DATA SHEET

|                                       |   |                         |                  |
|---------------------------------------|---|-------------------------|------------------|
| <b>Name :</b>                         | <b>PES 500D/64T PVC WR UV</b>   |                         |                  |
| <b>Supplier :</b>                     | KINETIC s.r.o.<br>SNP 9/6 ; 796 07Držovice<br>IČO:27728234 ; DIČ: CZ27728234<br>tel.: 582 365 770<br>email : kinetic@kinetic.cz             |                         |                  |
| <b>Manufactured :</b>                 | Taiwan  |                         |                  |
| <b>PROJECT</b>                        | <b>TESTING RESULTS</b>  | <b>TESTING STANDARD</b> | <b>TOLERANCE</b> |
| <b>Description</b>                    | PES 500D/64T PVC WR UV  |                         |                  |
| <b>Textile :</b>                      | 100% polyester  |                         |                  |
| <b>Lamination :</b>                   | PVC   |                         |                  |
| <b>Dyeing method:</b>                 | Sollution dyeing  |                         |                  |
| <b>Weight :</b>                       | 442,27  | ISO 3801 (g/m2)         | +/- 5%           |
| <b>Dimensions :</b>                   | fabric width 58" - length 1 roll 50m  |                         | +/- 5%           |
| <b>Tensile strength:</b>              |   |                         |                  |
| <b>warp</b>                           | 1432.73   | ISO 13934-1 (N)         | +/- 5%           |
| <b>weft</b>                           | 1313.65   | ISO 13937-2 (N)         | +/- 5%           |
| <b>Tear strength:</b>                 |   |                         |                  |
| <b>warp</b>                           | 86.32   | ISO 13937-2 (N)         | +/- 5%           |
| <b>weft</b>                           | 71.75   |                         | +/- 5%           |
| <b>Abrasion resistance :</b>          | 50 000  | ATCC-127 (cycles)       | +/- 5%           |
| <b>Water column :</b>                 | 2498  | ATCC-127 (mmH2O)        | +/- 5%           |
| <b>Others</b>                         |   |                         |                  |
| <b>Laundry symbols :</b>              | <br>DO NOT WASH    DO NOT BLEACH    DO NOT TUMBLE DRY    DO NOT IRON    DO NOT DRY CLEAN  |                         |                  |
| <b>Suitable method of treatment :</b> | Textile side of the fabric clean either dry with a soft brush or slightly wet cloth<br>The fabric should be left to dry at room temperature |                         |                  |
| <b>Recommended</b>                    | Recommended to store in a horizontal position, in a dry and well-ventilated area, away from   |                         |                  |
| In Drzovice 1.10.2024                 |   |                         |                  |