








KINETIC s.r.o  
SNP 9/6  
796 07 Držovice

+420 582 365 770 kinetic@kinetic.cz



## TECHNICAL DATA SHEET

Name :	PES 600/300D/99T WR PU UV					
Supplier :	KINETIC s.r.o. SNP 9/6 ; 796 07Držovice IČO:27728234 ; DIČ: CZ27728234 tel.: 582 365 770 email : kinetic@kinetic.cz					
Manufactured :	ROC					
PROJECT	TESTING RESULTS	TESTING STANDARD	TOLERANCE			
Description	PES 600/300D/99T WR PU UV					
Dyeing method:	Sollution dyeing					
Textile :	<u>100% polyester</u>					
Lamination :						
Weight :	262	ISO 3801 (g/m2)	+/- 5%			
Dimensions :	fabric width 58" - length 1 roll 50m		+/- 5%			
Tensile strength:		ISO 13934-1 (N)				
warp	2029.84		+/- 5%			
weft	918.39		+/- 5%			
Tear strength:		ISO 13937-2 (N)				
warp	88.67		+/- 5%			
weft	39.92		+/- 5%			
Abrasion resistance :	>90000	ISO 12947-2	+/- 5%			
Water column :	1843	EN 20811 (mmH2O)	+/- 5%			
Others	Certificate of compliance with the REACH regulation, confirming that the product meets the principles of the European Union directive REACH 1907/2006. OEKO-TEX® STANDARD 100 <b>Certifikate:</b> PG015 281880					
Laundry symbols :	    	DO NOT WASH	DO NOT BLEACH	DO NOT TUMBLE DRY	DO NOT IRON	DO NOT DRY CLEAN
Suitable method of treatment :	Textile side of the fabric clean either dry with a soft brush or slightly wet cloth The fabric should be left to dry at room temperature					
Recommended	Recommended to store in a horizontal position, in a dry and well-ventilated area, away from sunlight and UV radiation					
	In Drzovice 14.4.2026					