KINETIC s.r.o
SNP 9/6
796 07 Držovice
+420 582 365 770 kinetic@kinetic.cz

TECHNICAL DATA SHEET

Name :	**PES UV BEZ ZÁTĚRU MELANGE**		
Supplier :	KINETIC s.r.o. SNP 9/6 ; 796 07Držovice IČO:27728234 ; DIČ: CZ27728234 tel.: 582 365 770 email : kinetic@kinetic.cz		
Manufactured :	ROC		
PROJECT	TESTING RESULTS	TESTING STANDARD	TOLERANCE
Description	PES UV BEZ ZÁTĚRU MELANGE		
Dyeing method:	Sollution dying		
Textile :	100% polyester		
Lamination :			
Weight :	266	ISO 3801 (g/m2)	+/- 5%
Dimensions :	fabric width 58" - lenghth 1 roll 40m		+/- 5%
Tensile strength:			
warp	1310.83	ISO 13934-1 (N)	+/- 5%
weft	1060.52		+/- 5%
Tear strength:			
warp	137.07	ISO 13937-2 (N)	+/- 5%
weft	121.00		+/- 5%
Abrasion resistance :		ISO 12947-2	+/- 5%
Water column :	90	EN 20811 (mmH2O)	+/- 5%
Others	Certificate of compliance with the REACH regulation, confirming that the product meets the principles of the European Union directive REACH 1907/2006. OEKO-TEX® STANDARD 100 **Certifikate:** PG015 281880		
Laundry symbols :	 DO NOT WASH DO NOT BLEACH DO NOT TUMBLE DRY DO NOT IRON DO NOT DRY CLEAN		
Suitable method of treatment :	Textile side of the fabric clean either dry with a soft brush or slightly wet cloth The fabric should be left to dry at room temperature		
Recommended	Recommended to store in a horizontal position, in a dry and well-ventilated area, away from sunlight and UV radiation		
	In Drzovice 14.4.2026		