



KINETIC s.r.o
SNP 9/6
796 07 Držovice
 ☎+420 582 365 770 kinetic@kinetic.cz



TECHNICAL DATA SHEET

Name :	PES 500/300D/64T PVC		
Supplier :	KINETIC s.r.o. SNP 9/6 ; 796 07Držovice IČO:27728234 ; DIČ: CZ27728234 tel.: 582 365 770 email : kinetic@kinetic.cz		
Manufactured :	ROC		
PROJECT	TESTING RESULTS	TESTING STANDART	TOLERANCE
Description	PES 500/300D/64T PVC		
Dyeing method:	Piece dyeing		
Textile :	<u>100% polyester</u>		
Lamination :	PVC granulat		
Weight :	365g/m2	ISO 3801 (g/m2)	+/- 5%
Dimensions :	fabric width 58" - length 1 roll 40m		+/- 5%
Tensile strength:			
warp	0	ISO 13934-1 (N)	+/- 5%
weft	0	ISO 13937-2 (N)	+/- 5%
Tear strength:			
warp	0	ISO 13937-2 (N)	+/- 5%
weft	0		+/- 5%
Water column :	0cm	ATCC-127 (mmH2O)	+/- 5%
Abrasion resistance :		ISO 12947-2 (Cycles)	+/- 5%
Others			
Laundry symbols :	 DO NOT WASH DO NOT BLEACH DO NOT TUMBLE DRY DO NOT IRON DO NOT DRY CLEAN		
Suitable method of treatment :	Textile side of the fabric clean either dry with a soft brush or slightly wet cloth The fabric should be left to dry at room temperature		
Recommended	Recommended to store in a horizontal position, in a dry and well-ventilated area, away from sunlight and UV radiation		
In Drzovice 21.1.26			